

## **TECHNICAL SPECIFICATION: PLAM DENSIFIER**

Sodium-based densifying treatment for internal concrete cementitious surfaces

In the presence of a new industrial or "cloudy" concrete floor (e.g. in Pavilux<sup>®</sup> or Deco Nuvolato<sup>®</sup> Isoplam<sup>®</sup>), but with at least 7 days of life, wash it with Isoplam<sup>®</sup> **Plam Apripori** acid and rinse thoroughly.

In the case of seasoned concrete without treatments, wash with Isoplam<sup>®</sup> Plam Super Cleaner degreaser and rinse thoroughly.

Application of Isoplam<sup>®</sup> Plam Densifier, at a rate of approx. 0.2 0.3 L/m<sup>2</sup>, rubbing with Isoplam<sup>®</sup> white sponge disc applied to the Isoplam<sup>®</sup> Power trowel Machine, keeping the surface wet and continuing to massage for at least 30 minutes.

Thorough rinsing of the surface with a pressure washer or Isoplam<sup>®</sup> scrubber dryer and subsequent complete removal of the water with Isoplam<sup>®</sup> Professional squeegee.

Application of one coat of Isoplam<sup>®</sup> Antiolio Oil Repellent (approx. 0.1 L/m<sup>2</sup>), Isoplam<sup>®</sup> Metallic Wax (0.03 L/m<sup>2</sup>) or Isoplam<sup>®</sup> Plam Poly Wax (0.03 L/m<sup>2</sup>).

The price includes: the protection of parts not affected by the processing, the supply and transportation of materials to the construction site, the equipment and machinery for carrying out the work.

For a total of. ......  $m^2$  at the price of  $\in$  ........./ $m^2$